



TECHNICAL DATA SHEET

Order reference	OP150-DND-E
Article number	813733

Date	4-11-11	Replaces	03-31-08	No. Pages	1
-------------	---------	-----------------	----------	------------------	---

Product Description:

Style	Pads; perforated on centerline for dividing in half for smaller applications Packaging; "Dispense & Dispose" carton for easy pad access. Carton also contains two disposal bags for containment of used pads.
Item Size (each)	41 cm x 51 cm
Color	White
Composition	100% Polypropylene
Structure	96% natural white meltblown nonwoven fibers(<10 microns) 4% white spunbond nonwoven coverstock(<15-30 microns)
Technology	Meltblown + spunbond
Absorbency	Hydrophobic + Oleophilic
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Low -Lint Chemical Resistant Sorbent for Oil and Solvent Base Liquids
-----------------------------	---

Absorbency Capacity	168 l per bale (saturated; medium viscosity-12.5x)
----------------------------	--

Packaging Description:

Package configuration	1-Case	Pkg. Weight	14.0 kg (11.6 kg)
Items per Package	150 pads/Case	Pkg. Dimensions	54.5 cm x 45 cm x 64 cm H
Container type	Dispenser Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	g/m ²	365	36
Caliper	SPCTM-020	mm	5.3	0.5
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	daN	13.8	1.3
Color	Visual	-----	White	per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. ** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.